

* NOTICES *


Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] a) Following formula,



polymer with the polycarbonate structure of having the repeat unit expressed with (R is the hydrocarbon group of the shape of a straight chain of carbon numbers 2-20, and the letter of branching), and b -- the thermally conductive pressure sensitive adhesive characterized by including the thermally conductive filler of the rate which serves as the 10 - 300 weight section to this polymer 100 weight section

[Claim 2] The thermally conductive pressure sensitive adhesive according to claim 1 with which polymer with the polycarbonate structure of a component consists of with a weight average molecular weight of 10,000 or more compounded from the dicarboxylic-acid component which made indispensable the dicarboxylic acid to which the diol component which made the polycarbonate diol indispensable, and a carbon number make a molecule skeleton the hydrocarbon group of the aliphatic series of 2-20, or an alicycle group polyester.

[Claim 3] The adhesion sheets which come to prepare the layer of a thermally conductive pressure sensitive adhesive according to claim 1 or 2 in one side or both sides of a thermally conductive base material

[Translation done.]